



EXPLORE MOON *to* MARS

# Advancement of Novel Additively Manufactured Alloys for Space Applications

*Paul Gradl, Chris Protz, Alison Park Colton Katsarelis*  
**National Aeronautics and Space Administration (NASA)**

7 March 2022

1st International Conference on Advanced Manufacturing for Air, Space and Land Transportation



# Agenda




- Introduction and need for AM
- New alloys for propulsion applications
  - NASA HR-1 and JBK-75
  - GRCop-42 and GRCop-84
- Types of AM Processes
- Examples of components developed with alloys
- High duty cycle testing of alloys
- Summary



# The Case for Additive Manufacturing in Propulsion



- Metal Additive Manufacturing (AM) provides significant advantages for lead time and cost over traditional manufacturing for rocket engines
  - Lead times reduced by 2-10x
  - Cost reduced by more than 50%
- Complexity is inherent in liquid rocket engines and AM provides new design and performance opportunities
- **Materials that are difficult to process using traditional techniques, long-lead, or not previously possible are now accessible using metal additive manufacturing**





# Environment and Requirements for Rocket Engines



## Combustion chambers and regeneratively-cooled nozzles


- High heat flux and combustion temperatures ( $>3300\text{ }^{\circ}\text{C}$ ), high wall temperatures (wall  $T > 700^{\circ}\text{C}$ ), high chamber pressure (410 bar)
- Complex loads from thermal, static, and dynamic
- Compatibility with propellants (e.g. hydrogen)
- Thin-walls to maintain adequate wall temperatures
- High thermal gradients ( $>230^{\circ}\text{C}$  across hotwall)
- High conductivity
- Reusability – typically  $>50$  starts
- Minimize overall mass (high strength to weight)

**Require alloys that can be built using AM with complex internal features and maintain high strength at elevated temperatures with adequate fatigue life**

# High Strength Copper and H2 Resistant Alloys

**GRCop-42 / GRCop-84** for combustion chambers

- *High strength, high conductivity Cu-Cr-Nb alloy*



**NASA HR-1 and JBK-75** for nozzles and other components

- *Hydrogen resistant Fe-Ni-Cr high strength superalloys*



# AM Processes evaluated to produce components


Laser Powder Bed Fusion (L-PBF)



Laser Powder Directed Energy Deposition (LP-DED)



Cold Spray



Arc Wire Directed Energy Deposition (AW-DED)



# GRCop-alloys using Laser Powder Bed Fusion (L-PBF)

- Oxidation and blanching resistance during thermal and oxidation-reduction cycling.
- A maximum use temperature around 800°C, depending upon strength and creep requirements.
- Good mechanical properties at high use temperatures (2x of typical copper).
- Lower thermal expansion to reduce thermally induced stresses and low cycle fatigue (LCF).
- Established powder supply chain and commercial supply chain.
- Significant maturity in characterization and hot-fire testing (high TRL).








# Comparison GRCop-84 and GRCop-42



Element	GRCop-42 Wt %	GRCop-84 Wt %
Cu	Balance	Balance
Cr	3.1 – 3.4	6.2 – 6.8
Nb	2.7 – 3.0	5.4 – 6.0
Fe	Target <50 ppm	Target <50 ppm
O	Target <250 ppm	Target <250 ppm
Al	Target <100 ppm	Target <100 ppm
Si	Target <100 ppm	Target <100 ppm
Cr:Nb Ratio, %wt	1.13 – 1.18	1.13 – 1.18



## GRCop-42 and GRCop-84 for different applications:

- GRCop-42 has improved thermal conductivity (20-30%)
- GRCop-84 has slightly higher strength and improved LCF properties
- GRCop-42 has matured supply chain and lower cost
- Both only require Hot Isostatic Pressing (HIP) post-build



- NASA has advanced bimetallic and multi-alloy GRCop-alloy to superalloy AM for combustion chambers for radial and axial joints
- Advancements were made through evaluations of various multi-alloy AM processes, material characterization, and successful component manufacturing and hot-fire testing



LP-DED Jacket



Cold spray Jacket





Direct Deposit NASA HR-1 Nozzle



EBW-DED Jacket



# Hot-fire Testing and Development

- High TRL and maturity of material properties and component development
- Completed hot-fire testing using propellants LOX/H<sub>2</sub>, LOX/RP-1, LOX/CH<sub>4</sub> and thrust classes 8.9 to 155.7 kN (chamber pressures >96 bar)
- Over 40,933 seconds of hot-fire time and 1,010 starts on >30 chambers
- Single chamber unit achieved 296 starts and >10,600 seconds and another unit achieved 168 starts and >7,400 sec – remain in excellent condition
- Peak temperatures >727°C




# NASA HR-1 Alloy developed for LP-DED Process

- NASA HR-1 is an Fe-Ni-Cr alloy developed for high pressure hydrogen environments.
- Derived from JBK-75 and designed for higher strength and improved weldability
- Reformulated for AM LP-DED to reduce titanium segregation.
- Advanced using LP-DED at different deposition rates to allow for variations in wall thickness and deposition time.
- Recently optimized heat treatments to mitigate  $\eta$ -phase and improve properties.





# Various Components Fabricated using LP-DED





# LP-DED NASA HR-1 and JBK-75 Nozzles



NASA HR-1

**1.52 m diameter and 1.78 m height with integral channels**  
90 day deposition




JBK-75

**2.41 m dia and 2.82 m height**  
Near Net Shape Forging Replacement



# Hot-fire Testing of NASA HR-1 and JBK-75

- Completed various hot-fire test series with LOX/H<sub>2</sub> and LOX/CH<sub>4</sub> at 8.9 to 35.6 kN (chamber pressures >76 bar)
- Accumulated >14,876 sec and >400 starts on NASA HR-1 and JBK-75 AM nozzles
- NASA HR-1 integral channel unit 207 starts and >6,976 sec and JBK-75 with 114 starts and >4,170 seconds
- Wall temperatures exceeding 732°C





- High performance chambers and nozzles in extreme environments require novel alloys.
- NASA has matured GRCop-42, GRCop-84, NASA HR-1 and JBK-75 using L-PBF and LP-DED.
- AM processes producing geometry and material properties required have matured.
- NASA has demonstrated high duty cycle hot-fire tests on a GRCop-42 L-PBF combustion chamber with 296 starts and NASA HR-1 LP-DED nozzle with 207 starts.
- Commercial space is actively using these alloys for development and flight infusion.
- Data and properties available to commercial and government partners.





Contact:

Paul Gradl

NASA MSFC

+1 256.544.2455

Paul.R.Gradl@nasa.gov





# Acknowledgements



This paper describes objective technical results and analysis. Any subjective views or opinions that might be expressed in the paper do not necessarily represent the views of the National Aeronautics and Space Administration (NASA) or the United States Government.

John Fikes  
Auburn University  
National Center for Additive  
Manufacturing Excellence (NCAME)  
Mike Ogles  
Nima Shamsaei  
Drew Hope  
Matt Melis  
RPM Innovations (RPMI)  
Tyler Blumenthal / RPMI  
DM3D  
Bhaskar Dutta / DM3D  
Rem Surface Engineering  
Procam  
Powder Alloy Corp  
Tal Wammen  
Scott Chartier  
Test Stand 115 crew  
Kevin Baker  
Matt Medders  
Adam Willis

Dale Jackson  
Marissa Garcia  
Nunley Strong  
Gregg Jones  
Marissa Garcia  
Dwight Goodman  
Will Brandsmeier  
Jonathan Nelson  
Bob Witbrodt  
Shawn Skinner  
Megan Le Corre  
Will Evans  
John Ivester  
John Bili  
Will Tilson  
Zach Jones  
Dave Ellis  
Jim Lydon  
Judy Schneider / UAH  
PTR-Precision Technologies  
Westmoreland Mechanical Testing

David Myers  
Ron Beshears  
James Walker  
Steve Wofford  
Jessica Wood  
Robert Hickman  
Johnny Heflin  
Mike Shadoan  
Keegan Jackson  
Many others in Industry, commercial space and  
others



# References



- Gradl, P. “Rapid Fabrication Techniques for Liquid Rocket Channel Wall Nozzles.” AIAA-2016-4771, Paper presented at 52nd AIAA/SAE/ASEE Joint Propulsion Conference, July 27, 2016. Salt Lake City, UT.
- Gradl, P. R., & Protz, C. S. (2020). Technology advancements for channel wall nozzle manufacturing in liquid rocket engines. *Acta Astronautica*, 174, 148-158.  
<https://doi.org/10.1016/j.actaastro.2020.04.067>
- Gradl, P.R., Greene, S.E., Brandsmeier, W., Johnston, I. Hot-fire Testing and Large-scale Deposition Manufacturing Development Supporting Liquid Rocket Engine Channel Wall Nozzle Fabrication, Paper presented at 65th JANNAF Propulsion Meeting/10th Liquid Propulsion Subcommittee, May 21-24, 2018. Long Beach, CA.
- Kerstens, F., Cervone, A., Gradl, P. (2021). End to end process evaluation for additively manufactured liquid rocket engine thrust chambers. *Acta Astronautica*. 182, 454-465.  
<https://doi.org/10.1016/j.actaastro.2021.02.034>
- Gradl, P., Greene, S., Protz, C., Bullard, B., Buzzell, J., Garcia, C., Wood, J., Osborne, R., Hulka, J. Cooper, K. Additive Manufacturing of Liquid Rocket Engine Combustion Devices: A Summary of Process Developments and Hot-Fire Testing Results. 54th AIAA/SAE/ASEE Joint Propulsion Conference, AIAA Propulsion and Energy Forum, (AIAA 2018-4625). July 9-12, 2018. Cincinnati, OH.
- Gradl, P., Protz, C., Cooper, K., Garcia, C., Ellis, D., Evans, L. GRCop-42 Development and Hot-fire Testing using Additive Manufacturing Powder Bed Fusion for Channel-cooled Combustion Chambers. 55th AIAA/SAE/ASEE Joint Propulsion Conference, AIAA Propulsion and Energy Forum. August 19-21, Indianapolis, IN. AIAA-2019-4228
- Gradl, P., Protz, C., Wammen, T. Additive Manufacturing Development and Hot-fire Testing of Liquid Rocket Channel Wall Nozzles using Blown Powder Directed Energy Deposition Inconel 625 and JBK-75 Alloys. 55th AIAA/SAE/ASEE Joint Propulsion Conference, AIAA Propulsion and Energy Forum. August 19-21, Indianapolis, IN. AIAA-2019-4362
- Gradl, P., Protz, C., Fikes, J., Clark, A., Evans, L., Miller, S., Ellis, D.L., Hudson, T. Lightweight Thrust Chamber Assemblies using Multi-Alloy Additive Manufacturing and Composite Overwrap. AIAA Propulsion and Energy Forum. August 24-26. Virtual. (2020). AIAA-2020-3787.
- ASTM International. (2016). *ASTM F3187 - 16 Standard Guide for Directed Energy Deposition of Metals*. ASTM.Org. <https://www.astm.org/Standards/F3187.htm>
- Anderson, R., Terrell, J., Schneider, J., Thompson, S. and Gradl, P., 2019. Characteristics of Bi-metallic Interfaces Formed During Direct Energy Deposition Additive Manufacturing Processing. *Metallurgical and Materials Transactions B*, pp.1-10.
- Onuike, B., Heer, B. and Bandyopadhyay, A., 2018. Additive manufacturing of Inconel 718—copper alloy bimetallic structure using laser engineered net shaping (LENS™). *Additive Manufacturing*, 21, pp.133-140.
- Bandyopadhyay, A. and Heer, B., 2018. Additive manufacturing of multi-material structures. *Materials Science and Engineering: R: Reports*, 129, pp.1-16
- Gradl, P., Protz, C., Wammen, T. “Additive Manufacturing Development and Hot-fire Testing of Liquid Rocket Channel Wall Nozzles using Blown Powder Directed Energy Deposition Inconel 625 and JBK-75 Alloys”. 55th AIAA/SAE/ASEE Joint Propulsion Conference, AIAA Propulsion and Energy Forum. August 19-22. Indianapolis, IN. (2019).
- Gradl, P., Mireles, O. and Andrews, N., 2019. Introduction to Additive Manufacturing for Propulsion Systems. M19-7605. AIAA Propulsion and Energy Forum and Exposition; August 19, 2019 - August 22, 2019; Indianapolis, IN; United States. [10.13140/RG.2.2.13113.93285](https://doi.org/10.13140/RG.2.2.13113.93285)
- Hauser, C. Additive Manufacturing Seminar: Blown Powder Activities. TWI Materials and Joining Technologies. Retrieved from: [www.twi-global.com/\\_resources](http://www.twi-global.com/_resources). (2015)
- Karczewski, K., Pęska, M., Ziętała, M. and Polański, M., 2017. Fe-Al thin walls manufactured by laser engineered net shaping. *Journal of Alloys and Compounds*, 696, pp.1105-1112.





# References



- K.S. Chan, M. Koike, R.L. Mason, and T. Okabe, Fatigue Life of Titanium Alloys Fabricated by Additive Layer Manufacturing Techniques for Dental Implants, *Metall. Trans. A*, 2013, 44A, p 1010– 1022.
- DebRoy, T., Wei, H.L., Zuback, J.S., Mukherjee, T., Elmer, J.W., Milewski, J.O., Beese, A.M., Wilson-Heid, A., De, A. and Zhang, W., 2018. Additive manufacturing of metallic components—process, structure and properties. *Progress in Materials Science*, 92, pp.112-224.
- Sames, W.J., List, F.A., Pannala, S., Dehoff, R.R. and Babu, S.S., 2016. The metallurgy and processing science of metal additive manufacturing. *International Materials Reviews*, 61(5), pp.315-360.
- P. S. Chen, B. Panda, and B.N. Bhat, "NASA HR-1, A New Hydrogen Resistant Fe-Ni Base Superalloy", *Hydrogen Effects in Materials*, edited by A.W. Thompson and N.R. Moody, Minerals, Metals, and Materials Society (TMS), 1996.
- A.W. Thompson, J.A. Brooks, "Hydrogen Performance of Precipitation-Strengthened Stainless Steels Based on A-286." *Metallurgical Transactions A*, Vol. 6, No. 7, 1975, p. 1431. doi:10.1007/BF02641935.
- P.S. Chen, C.C. Katsarelis, W.M. Medders, P.R. Gradl, "Segregation Evolution and Diffusion of Titanium in DED NASA HR-1", NASA/TM–20210013649.
- M. Morinaga, N. Yukawa, and H. Adachi, "Alloying Effect on the Electronic Structure of Ni<sub>3</sub>Al ( $\gamma'$ )," *J. Phys. Soc. Japan*, 1984, vol. 53, No. 2, pp.653-63.
- M. Morinaga, N. Yukawa, H. Ezaki, "Solid Solubilities in Transition-Metal Based FCC Alloys," *Phil. Mag. A*, 51 (1985), No. 2, pp.223-246.
- M. Morinaga, N. Yukawa, and H. Adachi, and H. Ezaki, "New PHACOMP and Its Application to Alloy Design," *Superalloys, 1984*, edited by M. Gell, M.C.S. Kortovich, R.H. Bricknell, W. B. Kent and J.F. Radavich, The Metallurgical Society of AIME , 1984, pp.523-532.
- M. Morinaga, N. Yukawa, and H. Adachi, "Alloying Effect on the Electronic Structure of BCC Fe," *J. Phys. F: Met. Phys.* 15 (1985), pp. 1071-1084.
- "η-Phase TTP Diagram Development for DED NASA HR-1," Internal Research, NASA Marshall Space Flight Center, Huntsville, AL.
- "Progress in Thermal Process Development and Ti Segregation Mitigation for AM NASA HR-1," Internal Research, NASA Marshall Space Flight Center, Huntsville, AL.
- Katsarelis, C., Chen, P., Gradl, P., Protz, C., Jones, Z., Ellis, D., and Evans, L. Additive Manufacturing of NASA HR-1 Material for Liquid Rocket Engine Component Applications. *JANNAF Dec.*
- Chen, P., and Mitchell, M. "ALLOY NASA-HR-1." No. April 2005, 2005.
- Gradl, P.R., Protz, C. "Large-Scale Channel Wall Nozzle Development using DED and LWDC Additive Manufacturing Techniques." Paper presented at 2019 JANNAF 11th Liquid Propulsion Subcommittee (LPS), December 9-13. Tampa, FL. (2019).
- Gradl, P. R., Protz, C., Fikes, J., Clark, A., Evans, L., Miller, S., Ellis, D., & Hudson, T. (2020). Lightweight thrust chamber assemblies using multi-alloy additive manufacturing and composite overwrap. *AIAA Propulsion and Energy 2020 Forum*, 1–25. <https://doi.org/10.2514/6.2020-3787>



# Comparison of GRCop-84 and GRCop-42







# Large scale Integrated Channel DED NASA HR-1 Nozzle



60" (1.52 m) diameter and 70" (1.78 m) height with integral channels  
90-day deposition